

DuPont™ Oasis® 200TRT515

Composite Film

Product Description

Oasis® 200TRT515 is a heat sealable composite film that is made using DuPont high tensile strength polyimide film and fluoropolymer designed to meet the normal weight wire requirements of AS22759/80-92. 200TRT515 film has a unique balance of excellent electrical, thermal durability, and chemical resistance properties, including improved hydrolytic stability, that make it ideal for the next generation of aerospace wire designs.

200TRT515 film possesses excellent bonding characteristics to itself and to other fluoropolymer-containing materials, while providing low adhesion to metal conductors for ease of stripping. These unique bonding characteristics should provide a wide operating window for producing modern composite wire insulations.

This material can be processed on most taping machines designed to wrap polyimide based films around electrical conductors.

Applications

Aerospace Wire and Cable

- airframe wires
- hookup wires
- general purpose aircraft wires

Specialty Wires

- magnet wire
- satellite wire

Packaging

Oasis® 200TRT515 composite film is available in various standard roll packages. Custom roll packages can be produced with applicable upcharges. Contact your regional sales representative for additional information.

Additional product information, processing requirements and the safe handling of Oasis® can be found in Bulletin EI-10169.

Table 1. Typical Properties of Oasis® 200TRT515 Film

Property	Units	Typical Value	Test Method
Thickness	mil	2.00	ASTM D374
Density	g/cc	1.81	ASTM D1505
Tensile Strength	kpsi	30	ASTM D882
Tensile Modulus	kpsi	480	ASTM D882
Elongation	%	70	ASTM D882
Moisture Content	%	<1.0	DuPont Test Method
Heat Seal Strength at 350°C	g/cm	500	DuPont Test Method
Seal Initiation Temperature	°C	280	DuPont Test Method
Dielectric Strength	V/mil	4600	ASTM D149
Dissipation Factor at 1 kHz	-	0.010	ASTM D150
Dielectric Contant at 1 kHz	-	2.85	ASTM D150
Volume Resistivity	ohm-cm	10 ¹⁶	ASTM D257
Yield	ft ² /lb	53.2	DuPont Test Method

DuPont™ Oasis® 200TRT515

Composite Film



electronics.dupont.com

For more information on DuPont™ Oasis® composite film or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Applications CAUTION" and "DuPont Medical Applications POLICY" statements. These documents are available upon request.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

EI-10163 (5/21)